



6070

Primer Sealer
Super Hide
Acrylic latex

Technical Data Sheet

INTERIOR

DESCRIPTION

Proline 6070 is a high build acrylic latex primer sealer for indoor use. It is easy to apply, without spattering and dries quickly. It is formulated to seal new drywall. Tintable bases are available to be coloured. This primer was developed to answer the needs of professional painters. The Proline 6070 can be used for commercial, industrial and residential projects.

USE

This super hide primer sealer is applicable on interior surfaces. It seals and hides repairs in order to obtain a uniform finish once the topcoat is applied. Proline 6070 is recommended for new surfaces such as drywall, concrete, and wood.

ADVANTAGES

- Proline 6070 was developed to seal drywall as well as repairs in order to obtain a uniform finish once topcoated.
- It dries quickly and can be covered after only 3 hours.
- It provides an excellent hiding
- Low spattering. during application, minimal protection is required for baseboards and flooring
- Can easily be sanded after a drying time of 3 hours without overloading the sanding paper.
- Tintable bases are used as a primer for colours lacking hiding power
- Certified MPI

LIMITATIONS

- Avoid application under 10°C
- Not for exterior application
- Do not use on flooring
- Do not apply on alkyd paint

TECHNICAL DATA

| | | | |
|----------------------------|------|---|-----|
| Resin | | Acrylic Latex | |
| Color | | White | |
| Cleaning | | Water | |
| Flash point | | N/A | |
| Inflammability | | N/A | |
| Solids by weight | | 58+/-2 | % |
| Solids by volume | | 44+/-2 | % |
| VOC | | <50 | g/l |
| Gloss | 60° | N/A | % |
| Sheen | 85° | N/A | % |
| Standards / Certifications | LEED | Eligible for LEED® v4 CDPH Emissions Certified | |
| | MPI | Certified Category #50, GPS-1, GPS-2 | |
| | CFIA | Approved | |

APPLICATION DATA

| | | | | |
|--|-------------------------------|---------------|--------------------|-------|
| At 25° Celsius | | | | |
| Relative humidity at 50% | | | | |
| May differ depending on the colour | | | | |
| Spreading Rate | May | 37-46 m2 | gallon | |
| <small>vary depending on the surface</small> | | (300-400sqft) | | |
| Film Thickness | Wet | 3,2-4,0 | mils | |
| | Dry | 1,41-1,76 | mils | |
| Drying Time | Tack free | 30 | min | |
| | Recoat | 4 | hours | |
| | Cleaning | N/A | days | |
| | Cure | 30 | days | |
| Application | Brush | √ | | |
| | Roller | 15 | mm | |
| | Spray* Nozzle: 0.017 - 0.021* | 2000-2500 | lb/po ² | |
| <small>Max dilution 10%</small> | | | | |
| <small>* These data may vary depending on the equipment manufacturer</small> | | | | |
| Exterior | | N/A | | |
| Storage | Temperature | 10-30 | °C | |
| Tinted Bases | Formats | | | |
| | | 946ml | 3,78L | 18,9L |
| | 6070-0 White | | √ | √ |
| | 6070-0 Base M | | √ | |
| 6070-0 Base D | | √ | | |
| <small>max. 8 oz of colorant /3,78 L</small> | | | | |
| <small>max. 11 oz de colorant /3,78 L</small> | | | | |



6070
Primer Sealer
Super Hide
Acrylic latex

Technical Data Sheet

INTERIOR

SURFACE PREPARATION

The surface must be dry and clean, without dust, oil, grease, rust and soap. On painted surfaces, it is recommended to clean with a degreaser (T.S.P.) in order to eliminate any contaminant that may harm the adhesion or the curing of the product. Thoroughly rinse the entire surface. The surfaces must be well sanded and dusted.

Presence of mold: Clean the affected area with a mixture of 1 part bleach to 3 parts water. Thoroughly rinse the entire surface.

Flaking or peeling paint: Using a scraper, remove the weakened and/or loose paint, then sand the edges of the surface to make it smooth.

A repair compound should be used to fill holes and uneven surfaces. Sand with a grade #100 sanding paper.

New drywall: To avoid creating an undesirable texture on the drywall, the joint compound must not be sanded excessively.

Concrete / Masonry: Wait until the concrete and/or masonry has cured at least 30 days before painting it.

Wood: The surface must be sanded with a grade #80 or #100 sanding paper to improve adhesion.

APPLICATION

This product is ready to be used and does not require dilution. Mix well before use. Apply one coat or two if necessary. Allow a minimum drying time of 4 hours between each coat for pale colours and 8 hours for dark colours. In order to properly cover the surface, it is recommended to use a 15mm lint free roller and a quality nylon-polyester brush. Clean the brushes and rollers with lukewarm soapy water following their use.

For spray application: May be diluted with a maximum of 10% water.

Pressure: 2000 to 2500 lb/in²*

Nozzle: 0.017 – 0.021*

*This data may vary depending on the brand of the equipment manufacturer.

MAINTENANCE

Must be topcoated.

WARRANTY

This product will give full satisfaction if applied according to the manufacturer's instructions. Manufacturer's liability is limited to the replacement of the product and does not include manpower if found defective upon inspection.

CAUTION

- Keep away from children's reach
- Keep lid closed when not in use
- Avoid freezing

Contact your municipality to dispose of the container in an environmentally-friendly manner.